

Jawad Kadhim Abaies

Saturday, December 18, 2010
12:21 AM

Study of Molecular Interactions of Water- Soluble Polymer at Several Temperatures in Solution

*Jawad Kadhim Abaies**

Date of acceptance 18/ 2/ 2009

Abstract:

Molecular interactions between 2-isopropenylnaphthalene-methacrylic acid (IPNMA) block copolymer (as a model for water-soluble polymer) and methanol at several temperatures were studied using fluorescence techniques. Fluorescence spectrum for (IPNMA) exhibits two emission bands at around 342 nm and 387 nm corresponding to the monomer and the excimer bands, respectively. The fluorescence spectra of dilute solution of (IPNMA) in methanol were recorded in temperature range of 8- 45°C. Plot of the excimer to monomer intensity ratio I_e/I_m versus temperature was obtained, which shows double lines with positive slopes crossing at 25°C, the increasing of slope value above this temperature is small which indicates that there is stronger solvation of methanol molecules to polymer coil at temperature below 25°C arising from hydrogen bond formation between the polymer and the solvent.

Key words : (fluorescence spectroscopy , excimer , molecular interaction , polymer conformation, temperature- dependence).

Introduction:

Water-soluble polymers are added to many commercial products, such as paints, inks, cosmetics, food-stuff, and water-borne coatings [1]. In recent years, interest in these polymers has been rejuvenated, as a consequence of the growing concerns about the safety of more traditional organic-based fluids. They also can be used as analogues in understanding the behavior of biological macromolecules. Amphiphilic copolymers which contain hydrophobic and hydrophilic segments in the same molecule, in particular, are effective in this role [2].

Fluorescence spectroscopy (especially excimer fluorescence) has been found to be a versatile technique for investigations of the polymer properties. Many polymers with aromatic chromophores exhibit intra-

molecular excimer fluorescence. Excimer is excited-state complex formed by a couple of aromatic rings placed face to face at a short distance. The formation of excimer is due to association of two aromatic groups one of which has electronically excited [3]. It is characteristic for excimer fluorescence to appear in a considerably lower energy region than monomer fluorescence.

In last two decades, many researches have been carried out for investigation of this kind of polymers. Using excimer fluorescence.

Strauss and Vesnaver [4] used fluorescence technique to investigate microenvironment and conformational transitions of copolymer of maleic anhydride and alkyl vinyl ether. Morawetz and co-

*Department of Chemistry, College of science, University of Wasit

workers[5,6] have reported kinetics of the cooperative complex formation and dissociation of poly (Acrylic acid) and poly(ethylenc oxide). They have also studied the conformational transitions of poly (methacrylic acid) after change of its degree of ionization .

Turro and Okubo[7] have investigated excimer formation in poly(styrenesulfonate). Watanabe and Matsuda [8] have studied properties of polystyrene-poly(methylmethacrylate) graft copolymer. Turro et.al[9] studied intramolecular interactions of some water-soluble polymers.

Excimer formation of 1-pyrenemethanol on polystyrene latex particles and aqueous phase was reported[10]. Guillete and Nowakowska[11] have investigated isomerization of provitamin D₃ by polymers containing pendant naphthalene group .

Gorochovceva and Makuska[12]synthesized and studied viscosity and solubility of chitosan-o-poly(ethylene glycol) graft copolymers in aqueous solutions at several PH .

Group of workers[13] have investigated the antimicrobial effect of a triglucsan /copolymer dentifrice on microorganisms from dental plaque , saliva and the tongue then compared the results with fluoride dentifrice.

Fusco et.al[14] reported that polymer (ethylene oxide)-poly(propylene oxide)-poly(ethylene oxide)(PEO-PPO-PEO) tri-block copolymers have amphilic characteristics and show thermoreversible gelation around body temperature and, therefore , are particularly suitable for biomedical applications such as drug delivery , and gene therapy.

The main purpose of present work is to investigate the fluorescence spectra of 2 -

Isopropenylnaphthalene - methacrylic acid block copolymer (as a model for water-soluble polymer) in methanol at several temperatures to report information on the solvation , interactions and conformational transitions of polymer chain in solution . The ratio of the emission intensities of excimer and monomer depend on intrinsic and extrinsic characteristics of the system , for example , solvent ,temperature ... etc[15]. They were studied here in the temperature range of 8-45°C.

Materials and Methods:

1 – Materials:

I. 2-Isopropenylnaphthalene-methacrylic acid block copolymer (IPNMA) with molecular weight of 10338 was already synthesized and purified according to general procedure [16].

II. Methanol of special quality for fluorescence measurements with purity >99.99% was purchased by Flucka company .

2 – Instruments

Fluorescence spectra were measured with a Jasco spectrofluorometer FP-770 .Fluorescence measurements were carried out with excitation wavelength of 280 nm with an excitation slit width of 3nm and emission wavelength of 300nm .

spectrofluorometer was connected to a water bath (Lauda , Germany) Digital thermometer type (Jenway PWA1 , UK) was used to measure the temperature . The temperature controlled within $\pm 0.1^{\circ}$ C during the measurements . The concentration of the polymer solution was 0.002 g/25ml.

Results and Discussion:

Figure (1) shows fluorescence spectrum of 2-Isopropenylnaphthalene and methacrylic acid block copolymer of (IPNMA) in methanol. The fluorescence spectrum of the polymer contain two bands at a about 342nm belong to monomer naphthalene group, and a broad, structure less, red- shifted one at 387nm. This structure less band resembles the emission band observed in previous works,[3,17] therefore this attributed to excimer emission. It was found that the excimer band independent on polymer concentration ;thus it originate from an intramolecular excimer,[18,19].




Figure 1: fluorescence spectrum of IPNMA block copolymer in methanol at room temperature

Temperature dependent fluorescence measurements are particularly interesting, they yield information on solvation, behavior and conformational transitions of the polymer chain coil.

Figure (2) shows fluorescence spectra of block copolymer (IPNMA) in methanol. As the temperature is raised, the intensities of the monomer and excimer decrease. However, the intensity of the monomer band decreases more with increasing temperature than that of excimer band.




Figure 2 : Fluorescence spectra of IPNMA block copolymer in methanol at several temperatures

The intensities of monomer band (I_m) and excimer one (I_e) in arbitrary units are given in Figure (3) as a function of temperature. The intensities of monomer band




Figure 3 : Temperature dependence of fluorescence intensity of excimer (I_e) and monomer (I_m) bands for IPNMA block copolymer in methanol

decrease linearly in the rang of 8-45°C, while the plot of those of excimer band Show two different linear lines crossing at 25°C. This indicates that excimer formation lead to decrease an excited monomer.

Sivadsan et.al[20] reported that the extent of intramolecular excimer formation (given by the parameter I_e/I_m) provides a measure of the statistical conformation of the polymer chain. A large value of I_e/I_m suggests polymer chain expansion whereas a small value of I_e/I_m suggests polymer chain contraction. However, plotting of I_e/I_m ratio as a function of temperature given in

Figure 4, which shows double lines cross at ca. 25°C, above which the slope is




Figure 4 : Temperature dependence of the ratio of excimer to monomer fluorescence intensity of IPNMA block copolymer in methanol

small. The magnitude of increase in I_e/I_m with increasing temperature is related to the extent of solvation of solvent molecules to polymer coil. The increase in I_e/I_m might be attributed to polymer chain expansion form, which facilitates a parallel arrangement (sandwich like) configuration between neighboring naphthalene groups, which is a necessary condition to form excimer [3]. Consequently, it may be presumed that the change in polymer conformation occurs at 25°C. Therefore, it is concluded that there is stronger solvation of methanol molecules to polymer coils at temperature 25°C arising from the molecular interaction especially, the hydrogen bonding between the solvent molecules and the polymer at about 25°C. Thus it may be presumed that the interaction as hydrogen bonds between carboxyl groups in the polymer and methanol are weakened and may be broken by increasing temperature above 25°C.

Conclusions:

The fluorescence spectrum of (IPNMA) block copolymer exhibits two emission bands at about 342nm and 387nm which are assigned to monomer naphthalene and excimer, respectively. From the temperature-dependent fluorescence spectra

measurements, plots of I_e/I_m versus temperature were obtained, which show two lines intersecting at a point ascribed to a transition temperature. It is reasonable to assume that intramolecular hydrogen bonds between carboxyl groups of the polymer and methanol may be broken at the transition temperature.

References:

1. Shalaby, S.W., McCormick, C.L. and Butler, G.B. 1991. Water-Soluble Polymers: Synthesis, Solution Properties and Applications, ACS Symposium series NO.467; American Chemical Society; Washington, DC, U.S.A.
2. Ringsdorf, H. and Simon, J. 1992. Hydrophobically-Modified Poly(N-isopropylacrylamides) in water: Probing of the microdomain Composition by Nonradiative Energy Transfer. *Macromolecules*, 25: 5353-5361.
3. Hirayama, F. 1963. Intramolecular Excimer Formation. I. Diphenyl and Triphenyl Alkanes. *J. Chem. Phys.*, 42: 3161-3170.
4. Strauss, U.P. and Vesnaver, G. 1975. Optical Probes in Polyelectrolytes Studies. I. Acid-Base Equilibria of dansylated Copolymers of Maleic Anhydride and Alkyl Vinyl Ethers. *J. Phys. Chem.*, 79: 1558-1561.
5. Bendar, B. and Morawetz, H. 1984. Kinetics of the Cooperative Complex Formation and Dissociation of poly(acrylic acid) and Poly(oxyethylene). *Macromolecules*, 17: 1634-1636.
6. Bendar, B. and Morawetz, H. 1985. Kinetics of the Conformational Transitions of Poly(methacrylic acid) after Changes of Its Degree of Ionization. *Macromolecules*, 18: 1940-1944.
7. Turro, N.J. and Okubo, T. 1982. Intramolecular Excimer Formation in

- Aqueous Solutions of Sodium Poly(styrenesulfonate). *J.Phys.Chem.*, vol.86,NO.9:1485-1487.
8. Watanabe, A. and Matsuda. M.1985. Dilute Solutions Properties of a Polystyrene-Poly(methylmethacrylate) Graft Copolymer Studied with the Emission Probe Technique. *Macromolecules*,18:273-277.
 9. Turro, N. J. and Arora. K.S. 1986. Pyrene as a Photophysical Probe for Intermolecular Interactions of water-soluble Polymers in Dilute Solutions. *Polymer* ,27,May:783-795.
 10. Nakashima, k.,kido. N., Yekta. A. and Winnik. M.A. 1997. Photoreactions on Latex Surface: Excimer Formation of 1-pyrenemethanol on Polystyrene Latex Particles. *J. Photochemistry and Photobiology A:Chemistry* 110 ,207-212.
 11. Nowakowska, M. and Guillet. J.E. 1997. Studies of the antenna Effect in Polymer Molecules 29. Isomerization of Provitamin D₃ Photosensitized by Polymers Containing Pendant Naphthalene Groups. *J. Photochemistry and Photobiology A:Chemistry* 107,189-194.
 12. Gorochovceva, N. and Makuska. R.2003. Synthesis and of Water-soluble chitosan-O-Poly(ethylene glycol) Graft copolymers. *J. Eurpolym.* 12.215-220.
 13. Daniel, H., Furgang. D., Markowitz. K., Sreenivasan. K. , De Vizio W., 2006. The Antimicrobial Effect of Triclosan/Copolymer Dentifrice on Oral Microorganisms in Vivo. *J. Am. Dent. Assoc.*, 137 (10):1406-1413.
 14. Fusco, S. , Borzacchiello. A. and Netti. P.A. 2006. perspective on : PEO-PPO-PEO Triblock Copolymers and their Biomedical Applications . *J. Bio. Comp. Polym.*21(2):149-146.
 15. Salom, C.,Hernandez-Fuentes. I and pierola. I.F.1989. Temperature – Dependence of Poly(phenylsiloxane) Fluorescence. 2. Comparison of Poly(methylphenylsiloxane)with Copolymers of methylphenyl siloxane and Dimethylsiloxane .*Macromolecules*,22:1874-1878.
 16. AL- Takrity, E.T. Synthesis of Poly(methacrylic acid) Bearing Fluoresces Quenching group .*Euro. Polym.J.*,31(4):383-385.
 17. Chandross, E.A. and Dempster. C.J. 1970 . Intermolecular Excimer Formation and Fluoresces Quenching in Dinaphthylalkanes .*J. Am. Chem. Soc.*92 (12) :3586-3593.
 18. Abaies, J. K. 1999. Fluoresces and Viscometric Studies of Conformations of Polymethacrylic Acid in Alcohol / Water Binary Mixtures Solutions. M.Sc. Thesis , College of Education- Ibn Al-haitham , Baghdad University .
 19. Abaies , J. K. 2009. Effect of Temperatures on Behavior of Block Copolymer of 2-Isopropenylnaphthalene and Methacrylic Acid . J. Wassit University for Science and Medicine. Vol:1.No.1(accepted for publication).
 20. Sivadsan, A.K., somasundaran. P. and Turro. N.J 1991 Fluorescence and Viscometry Study of Complexation of Poly(acrylic acid) with Poly(acrylamide) and Hydrolyzed Poly(acrylamide) . *Colloid Polym. Sci.*,269:131-137.

دراسة التآثرات الجزيئية لبوليمر ذو قابلية الذوبان في الماء على مدى عدة درجات حرارية في المحلول

جواد كاظم عبيس*

*قسم الكيمياء – كلية العلوم – جامعة واسط

الخلاصة:

تمت دراسة التآثرات الجزيئية بين 2-ايزوبروبيناييل نفتالين –حامض الميثاكريليك بلوك كوبوليمر والميثانول على مدى عدة درجات حرارية باستخدام تقنية الفلورة (الانبعاث) . اظهر طيف الفلورة لمحلول مخفف للبوليمر في الميثانول وجود حزمتي انبعاث عند الطول الموجي 342 نانومتر و 387 نانومتر يعودان الى مونومر النفثالين والاكسامير على التوالي . تم قياس اطياف الفلورة لمحلول البوليمر على مدى عدة درجات حرارية من 8- 45 م° وعند رسم نسبة شدة حزمة الانبعاث للاكسامير الى شدة حزمة الانبعاث للمونومر (I_0/I_m) كدالة لدرجة الحرارة ظهر وجود خطين بميل موجب يتقاطعان عند 25 م° ، فوق هذه الدرجة تكون الزيادة في الميل جدا قليلة هذا يعني وجود اذابة قوية للبوليمر من قبل جزيئات الميثانول عند درجة حرارة اقل من 25 م° تعزى هذه الاذابة الى التآثرات القوية وعلى الخصوص الاصرة الهيدروجينية بين جزيئات الميثانول والبوليمر حيث تكون على اشدها تحت 25 م° .