

# Synthesizing and Characterizing Some Pharmaceutical Resins Using Mannich Bases and Studying Their Biological Activity

**Tamador Ali Mahmood**  

Department of Chemistry, College of Science for Women, University of Baghdad, Baghdad, Iraq.

Received 30/08/2023, Revised 29/09/2023, Accepted 01/10/2023, Published Online First 20/05/2024



© 2022 The Author(s). Published by College of Science for Women, University of Baghdad.

This is an open-access article distributed under the terms of the [Creative Commons Attribution 4.0 International License](https://creativecommons.org/licenses/by/4.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

## Abstract

Mannich bases functional groups were used, which is considered an inventive phenol formaldehyde resin was created in this study. The project was divided into two phases. The first portion involves creating a monomer of Mannich bases through a condensation reaction. The reaction occurs between aromatic aldehyde (P-hydroxy benzaldehyde) and primary amines like (Metoclopramide, trimethoprim, 2-aminobenzothiazoly, sulfamethoxazole, and 4-amino antipyrine) and with minor amines such as Carbazol. By condensing Mannich bases made in part one with formaldehyde and phenol, the second stage included making phenol formaldehyde resin with Mannich bases. The synthesized resins (Phenol-formaldehyde) have been characterized. The characterization was done by (1H-NMR, and FT-IR) to determine the degree of biological activity associated with some of the active groups. Keywords: Carbazole, Mannich bases, phenol formaldehyde, polymerization and Resin.

**Keywords:** Biological activity, Carbazol, Mannich bases, Pharmaceutical Resins, Phenol formaldehyde.

## Introduction

Phenol formaldehyde (P.F.) resin is considered one of the extremely active resins, it can be gained from reacting phenol with formaldehyde<sup>1</sup>. This resin, and resin-adhesives owns several industrial applications, particularly in the production of important materials like plastics<sup>2</sup>. Phenol formaldehyde resin mostly display high thermal stability, and high-mechanical stability, as well as to whether stability. Thus, (P.F.) resins are helpful for using them in imbibition and adhesives is constrained by slow treating rate and rising necessary curing temperature compared to other thermosetting adhesives<sup>3</sup>. A novel sequence of phenol formaldehyde resin was organized in this work by reacting part of organic compound phenol, as well as to other organic compound formaldehyde to Mannich bases. The current type of reactions has a great significance due to their wide usages in pharmaceutical chemistry preparation and interaction<sup>4</sup>. They were intensively studied mostly

due to their applications in synthesis several compound especially organic materials particularly for manufacturing pharmaceutical, cosmetically, dyes, anti-bacterial, anti-cancer, anti-inflammatory, in addition to anti-convulsant<sup>5</sup>. Hence amine exactly secondary amine was employed in prepare bases like Mannich bases is carbazole. Carbazole derivatives are famous for their pharmacological activities<sup>6</sup>. It is obvious from the literature that the derivatives of carbazole moiety enjoy inclusive spectrum of pharmacological activities, such as antibacterial<sup>7</sup>, antitumor<sup>8</sup>, antifungal<sup>9</sup>, antioxidant antineoplastic, and larvicidal activity. Also carbazole along with its derivatives are a vital type of nitrogen inclosing aromatic heterocyclic compounds, own required electronic and charge transport characteristics, along with large  $\pi$ - conjugated system, and the numerous functional groups are simply presented into the structurally rigid carbazole ring<sup>10</sup>.

## Materials and Methods

The chemicals used, in the current study, were characterized in the Table 1 below:

**Table 1. Materials and their description**

| Materials                                         | Description                                                                                                                                             |
|---------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------|
| 1 Chemicals                                       | Some materials are purchased from Aldrich ND Fluka, others from Sigma, other parts were purchased from DDH, and Merch. All chemicals were not purified. |
| 2 Melting Point Apparatus Stuart Scientific SMP3. | Used to record the uncorrected melting-points apparatus.                                                                                                |
| 3 SHIMADZU FT-IR-8400                             | For Registering [(FT-IR)] spectrum                                                                                                                      |
| 4 FOURIER-TRANSFORM SPECTROSCOPY (FTIR)           | Employed to attain an infrared-spectrum of absorption with 4000-6000 cm <sup>-1</sup> spectral range.                                                   |
| 5 Bruker [(500 MHz) instrument]                   | For Consequently (1H-NMR) spectra determination using (DMSO-d <sub>6</sub> ) and (TMS)                                                                  |






At the Al-albait University in Jordan's Department of Chemistry, internal reference measurements were taken.

### The Mannich Base Synthesis Procedure<sup>1,2</sup>

Using round bottom flask, Carbazole (0.001 mol) Solution was mixed with a ten ml of Dimethyl-formamide. At the same time 0.002 mol of various amins like [(metoclopramide,,2-aminobenzothiazoly, sulfamethaxazole, 4-amino antipyrine, and trimethoprim)] and [p-hydroxy

benzaldehyde (0.002mol)] were added and then refluxed for five hours. The utilized solvent was evaporated, and the resulting residue was decanted into ice water while being constantly agitated. After being filtered, the precipitate from the DMSO was re-crystallized. Table 2 provides a list of the physical characteristics of the items (A-E).

**Table 2. Physical properties of prepared Mannich bases (A-E)**

| Comp.No. | Molecular Structure                                                                 | Color       | Yield % | FW                                                              | M. P. C° | Molecular weight |
|----------|-------------------------------------------------------------------------------------|-------------|---------|-----------------------------------------------------------------|----------|------------------|
| A        |  | Brown       | 60      | C <sub>33</sub> H <sub>35</sub> ClN <sub>4</sub> O <sub>3</sub> | 147-149  | 313.82           |
| B        |  | Yellow      | 70      | C <sub>26</sub> H <sub>19</sub> N <sub>3</sub> OS               | 165-167  | 150.2            |
| C        |  | Light brown | 76      | C <sub>10</sub> H <sub>11</sub> N <sub>3</sub> O <sub>3</sub> S | 148-150  | 253.27           |
| D        |  | white       | 65      | C <sub>30</sub> H <sub>28</sub> N <sub>4</sub> O <sub>2</sub>   | 175-177  | 205.25           |
| E        |  | Light brown | 40      | C <sub>33</sub> H <sub>31</sub> N <sub>5</sub> O <sub>4</sub>   | 152-155  | 292.29           |

### Phenol-Formaldehyde Synthesis: Procedures.<sup>2</sup>






### General

Through batch polymerization using a 6% catalyst, phenol-formaldehyde resin was created using 1to 2

as molar ratio for phenol, formaldehyde. While catalyst started in activating the reaction, phenol and formaldehyde were combined in a flask to create Mannich bases. Once the combination reached a

temperature of 70 °C, it was heated to 90 °C to recover the lost heat, and then the same process was used to produce it in 93–95 °C for an hour. Table 3 shows the physical characteristics of resin (Aa-Ee).

**Table 3. Physical properties data of prepared polymers (Aa-Ee)**


| Polymer No. | Polymer Structure                                                                   | Color      | Yield % | Molecular weight for repeated unit | Softening Point C <sup>0</sup> | Molecular formula for repeated unit                             |
|-------------|-------------------------------------------------------------------------------------|------------|---------|------------------------------------|--------------------------------|-----------------------------------------------------------------|
| Aa          |    | Dark gray  | 80      | 706.34                             | 215-218                        | C <sub>41</sub> H <sub>44</sub> ClN <sub>5</sub> O <sub>4</sub> |
| Bb          |    | Pale red   | 85      | 527.66                             | 190-192                        | C <sub>34</sub> H <sub>25</sub> N <sub>3</sub> O <sub>3</sub> S |
| Cc          |   | Red        | 80      | 658.74                             | 175-179                        | C <sub>37</sub> H <sub>30</sub> N <sub>4</sub> O <sub>6</sub> S |
| Dd          |  | Dark Brown | 75      | 610.72                             | 205-208                        | C <sub>38</sub> H <sub>34</sub> N <sub>4</sub> O <sub>4</sub>   |
| Ee          |  | Brown      | 70      | 695.29                             | 185-188                        | C <sub>41</sub> H <sub>37</sub> N <sub>5</sub> O <sub>6</sub>   |

## Results and Discussion

The current research focused on functional groups that had been generated from the synthesis of [phenol formaldehyde resin] which was modified by Mannich bases Eq. 1.

This project was divided into several sections. In section one, new Mannich bases were created through the reaction of caebazole, parahydroxybenzaldehyde, and various primary

amines (1–5), and their antifungal properties were tested.



Using appropriate spectral methods ( $^1\text{H-NMR}$ , FT-IR), the active groups and structures of freshly

produced materials were characterized and confirmed.

The results of [FT-IR spectrum for compound] (B) presented in Fig. 1 showed an absorption band at  $3105\text{ cm}^{-1}$  that belonged to {the (N-H) amide}, as well as bands at  $3051$ ,  $2812$ ,  $1643$ , and  $3475\text{ cm}^{-1}$  that were caused, respectively, by [the (C-H) aromatic, (C-H) aliphatic, [the (C=N)], and [the (O-H)] of phenol.




Figure 1. The FTIR results for prepaid material (B)

The result that presented in Fig. 2 which showed compound (E) FTIR spectra. The result approved showed absorption of  $\nu$  ( $\text{NH}_2$ ) for amine at  $3421$ ,  $3317\text{ cm}^{-1}$  and  $3468$  owing to  $\nu$  (O-H). Additional

packs occurred at  $1636$ ,  $3116$ ,  $1462$ ,  $3012$ , and  $(2931, 2831)\text{ cm}^{-1}$ . That packs are due to present of  $\text{U}(\text{C}=\text{N})$ ,  $\text{U}(\text{N-H})$ ,  $\text{U}(\text{C-N})$ ,  $\text{U}(\text{C-H})$  aromatic, and  $\text{U}(\text{C-H})$  aliphatic sequentially




Figure 2. The FTIR results for prepaid material (E)

$^1\text{H}$ -NMR spectra were used to verify the chemical shifts, multiplications, and pairing constants of the competently prepared derivatives.

Fig. 3 gives a presentation of the chemical (A[( $^1\text{H}$ -NMR) 's spectrum], The results showed signals at phenyl proton  $\delta$  6.91-8.21 ppm. 1H proton of NH-

C=O at  $\delta$  9.79 ppm, 2H protons of ( $\text{CH}_2\text{-N}$ ) were at around  $\delta$  3.53 ppm. 1 H proton of OH at  $\delta$  8.25 ppm, 1H proton of CH-N at  $\delta$  6.03 ppm, 3 H protons at  $\text{CH}_3\text{-}$  at  $\delta$  1.28 ppm, and 2H protons of  $\text{CH}_3\text{-CH}_2\text{-N}$ ,  $\delta$  2.27-2.73 ppm, 3 H protons at  $\text{CH}_3\text{-O}$ ,  $\delta$  3.84 ppm.




Figure 3. The results of ( $^1\text{H}$ -NMR) spectral for synthesized materials (A)

So ( $^1\text{H}$ -NMR) spectrum of compound (D) Fig. 4 exhibited signals in  $\delta$  6.95-8.12 ppm return to aromatic ring protons  $\delta$  (6.55) ppm return to (-NH), appeared signals in  $\delta$  (5.76) ppm belong to 4 H

protons of ( $-\text{CH}_2\text{-CH}_2-$ ).  $\delta$  2.72 ppm due to N- $\text{CH}_3$ ,  $\delta$  1.23 ppm due to ( $-\text{CH}_3$ ), 8.36 due to OH phenolic group, and 3.50 due to 1 H protons for N-CHN.  $\delta$  3.54 due to ( $-\text{CH}_2\text{-CH}_2-$ ).





Figure 4. The results of ( $^1\text{H}$ -NMR) spectral for synthesized materials (D)

**Section Two** was done through applying polymerization predominantly batch polymerization using phenol, and formaldehyde with the previously

made Mannich bases in section one, phenol formaldehyde (P.F.) resin (phenolic chelating polymers) was created, Scheme. 1.








**Scheme 1. Synthesis of phenol formaldehyde resin**

Several parameters were affects resin organization. The most common is a degree of condensation with affecting how the resin is organized as the aromatic phenol ring, involves the [ortho and para] positions that can condense with formaldehyde, but the para location is further likely to do so than the ortho position. In a typical aromatic ring, the presence of one para location and two ortho locations can result in the production of resin via the phenol process that used (phenol-formaldehyde). The reagents are able to produce additional formaldehyde resin with [ortho hydroxyl-methyl] groups particularly. Therefore,



excess ortho on para substituted positions in formaldehyde or methylol towards phenol (ortho) positions lead to more responsive useful groups or more unreacted par appositions in the period of handling treatment, which may shorten the time of treatment and rise the degree of cross-linking for cured {phenol formaldehyde} resin.<sup>1,3</sup>




Physical characteristics and spectroscopic data are typically used to define novel phenol formaldehyde resin derivatives in Tables 2 and 3.

**Table 2. Physical properties of prepared Mannich bases (A-E)**

| Comp<br>No. | Molecular Structure                                                                 | Color       | Yield<br>% | FW                     | M. P.<br>C° | Molecular<br>weight |
|-------------|-------------------------------------------------------------------------------------|-------------|------------|------------------------|-------------|---------------------|
| A           |    | Brown       | 60         | $C_{33}H_{35}ClN_4O_3$ | 147-149     | 313.82              |
| B           |    | Yellow      | 70         | $C_{26}H_{19}N_3OS$    | 165-167     | 150.2               |
| C           |   | Light brown | 76         | $C_{10}H_{11}N_3O_3S$  | 148-150     | 253.27              |
| D           |  | white       | 65         | $C_{30}H_{28}N_4O_2$   | 175-177     | 205.25              |
| E           |  | Light brown | 40         | $C_{33}H_{31}N_5O_4$   | 152-155     | 292.29              |

**Table 3. Physical properties data of prepared polymers (Aa-Ee)**

| Polymer<br>No. | Polymer Structure                                                                   | Color     | Yield<br>% | Molecular<br>weight for<br>repeated unit | Softening<br>Point C° | Molecular<br>formula for<br>repeated unit |
|----------------|-------------------------------------------------------------------------------------|-----------|------------|------------------------------------------|-----------------------|-------------------------------------------|
| Aa             |  | Dark gray | 80         | 706.34                                   | 215-218               | $C_{41}H_{44}ClN_5O_4$                    |
| Bb             |  | Pale red  | 85         | 527.66                                   | 190-192               | $C_{34}H_{25}N_3O_3S$                     |

|    |                                                                                   |            |    |        |         |                           |
|----|-----------------------------------------------------------------------------------|------------|----|--------|---------|---------------------------|
| Cc |  | Red        | 80 | 658.74 | 175-179 | $C_{37}H_{30}N_4O_6$<br>S |
| Dd |  | Dark Brown | 75 | 610.72 | 205-208 | $C_{38}H_{34}N_4O_4$      |
| Ee |  | Brown      | 70 | 695.29 | 185-188 | $C_{41}H_{37}N_5O_6$      |

Compound (Bb) FT-IR spectra Bands were presented in 3045, (2985,2831),1600, 3211,3309, and 1450)  $cm^{-1}$  the results are shown in Fig. 5, the

spectra bands were due to  $\nu(C-H)$  arom,  $\nu(C-H)$  aliph,  $\nu(C=C)$ , stretching band for  $\nu(N-H)$ ,  $\nu(O-H)$ , and  $\nu(C-N)$ .





Figure 5. The FTIR results for prepaid materials (Bb).

Compounded similarly (Ee), Fig. 6 displays bands at 3039, (2924, 2838),1651, 3267, 3430 and 1477  $cm^{-1}$


due to  $\nu(C-H)$  arom.,  $\nu(C-H)$  aliph.,  $\nu(C=N)$ ,  $\nu(N-H)$ ,  $\nu(O-H)$  and  $\nu(C-N)$  successively.



**Figure 6. The FTIR results for prepaid material (Ee).**

Fig. 7 offers an illustration of the compound (Aa), <sup>1</sup>H-NMR spectrum revealed signals at δ (5) ppm due to the ν (OH) phenolic group, δ (6.90-7.10) ppm due to aromatic-ring-protons, δ 8.51 ppm} due to the ν {-NH} , and δ (7.14-7.73) ppm

due to the 4H protons for N-CH<sub>2</sub>-CH<sub>2</sub>N. Moreover, signals for the CH<sub>2</sub>-OH) proton and (-CH<sub>2</sub>-) proton, respectively, occurred at (1.30) ppm and  $\delta$ (4.50-4.78)ppm .



**Figure 7. The results of (1H-NMR) spectral for prepared complex (Aa)**

The results of compound (Dd) presented <sup>1</sup>H-NMR spectral data in Fig. 8, the results display signals in δ(6.97-7.72) ppm belonging to aromatic-ring-proton, δ(9.57) ppm, due to OH phenolic group, δ

6.58 ppm due to (-NH),  $\delta(3.70)$  ppm because of (O-CH<sub>3</sub>). Consequently, signals exposed at  $\delta$  2.18-2.41 ppm belonging to (-CH<sub>2</sub>-) proton and  $\delta(4.50-4.78)$  ppm belonging to (CH<sub>2</sub>OH) proton.




Figure 8. The results of (<sup>1</sup>H-NMR) spectral for prepared complex (Dd)

Table 4. (FT-IR) spectrum for all product compounds

| Com. No. | $\nu$ C-H arom. $\text{cm}^{-1}$ | $\nu$ C-H aliph. $\text{cm}^{-1}$ | $\nu$ C=C $\text{cm}^{-1}$ | $\nu$ N-H $\text{cm}^{-1}$ | $\nu$ O-H $\text{cm}^{-1}$ | $\nu$ C-N $\text{cm}^{-1}$ | Others $\text{cm}^{-1}$                  |
|----------|----------------------------------|-----------------------------------|----------------------------|----------------------------|----------------------------|----------------------------|------------------------------------------|
| A.       | 3047                             | 2877                              | 1600                       | 3170                       | 3417                       | 1450                       | C=O<br>1670                              |
| B.       | 3051                             | 2812                              | 1604                       | 3105                       | 3475                       | 1489                       | (C=N) ring<br>1643<br>(C=N) ring<br>1652 |
| C.       | 3051                             | 2885-2981                         | 1620                       | 3143                       | 3417                       | 1450                       | (S=O)<br>1285                            |
| D.       | 3051                             | 2893                              | 1604                       | 3255                       | 3417                       | 1450                       | (C=O)<br>Amid 1670<br>(C=N)              |
| E.       | 3012                             | 2831                              | 1600                       | 3116                       | 3468                       | 1462                       | 1636<br>(C=O)                            |
| Aa.      | 2951                             | 2831                              | 1597                       | 3151                       | 3300                       | 1477                       | 1647                                     |
| Bb.      | 2985                             | 2831                              | 1600                       | 3212                       | 3309                       | 1450                       | (C=N)<br>1481<br>(C=N) ring<br>1643      |
| Cc       | 2951                             | 2831                              | 1597                       | 3151                       | 3305                       | 1481                       | (S=O)<br>1222                            |
| Dd.      | 2978                             | 2831                              | 1593                       | 3217                       | 3448                       | 1477                       | (C=O) amid<br>1750                       |
| Ee.      | 3039                             | 2924                              | 1597                       | 3267                       | 3430                       | 1477                       | (C=N) 1651                               |

### Section Three

Anti-bacterial activity is presented in part three. The activity and application of some generated materials were investigated using two types of bacteria gram


positive and gram negative *Staphylococcus aureus*, *Bacillus subtilis*, *Escherichia coli*, *Klebsiella ssp.*, *Acintobacter baumannii* as well as *Rhizosporium*. The results are presented in Table 5. Biological

activity was used to regulate the biological efficacy for potential use as pharmaceuticals or the rapeptic<sup>11, 12</sup>. In DMSO, which also acted as a control, all Mannich bases were dissolved. The findings demonstrated that created compounds have superior action against [gram positive and gram negative] bacteria than all other compounds developed for compound (4)<sup>13</sup>. Table 5 displays the potency of produced compounds counter to particular species in


the absence of other species<sup>14</sup>. Various inhibitory zones of varying sizes were seen for the investigated bacterial strains Fig. 9-18. Compound (4) displayed good and highest efficacy against all species of bacteria as well as Rhizosbarium thanks to the action of resin components. The inhibition zones that were created by each medicine under investigation are presented in Table .5.

**Table 5. The Results of Biological activity for some synthesized materials.**


| Compound  | The inhibition zone against some bacteria in mm at 10 mg/ml |                    |                |                        |                    |
|-----------|-------------------------------------------------------------|--------------------|----------------|------------------------|--------------------|
|           | Gram positive                                               |                    | Gram Negative  |                        | <i>Rizosporium</i> |
|           | <i>S. aureus</i>                                            | <i>B. subtilis</i> | <i>E. coli</i> | <i>Klebsiella ssp.</i> |                    |
| A         | -Ve                                                         | 16                 | -Ve            | 17                     | -Ve                |
| C         | 30                                                          | 17                 | 40             | -Ve                    | 13                 |
| D         | -Ve                                                         | 14                 | -Ve            | 16                     | 11                 |
| E         | 12                                                          | 20                 | 50             | -Ve                    | 12                 |
| Aa        | 11                                                          | 17                 | 33             | 16                     | 13                 |
| Cc        | 19                                                          | 16                 | 26             | 17                     | 12                 |
| Dd        | 12                                                          | 15                 | 21             | 18                     | 10                 |
| Ee        | 13                                                          | 15                 | 18             | 17                     | 12                 |
| Carbazole | 15                                                          | 14                 | 18             | 16                     | 13                 |




**Figure 9. Effect of compound (8, 12, 14, 15) in (staphylococcus aureus)**




**Figure 11. Effect of compound (9, 11, 13, 18) in (staphylococcus aureus)**




**Figure 10. Effect of compound (9, 11, 13, 18) in (staphylococcus aureus)**




**Figure 12. Effect of compound (9, 11, 13, 18) in (bacillus subtilis)**



**Figure 13.** Effect of compound (8, 10, 12, 14) in (*escherichia. coli.*)




**Figure 16.** Effect of compound (9, 11, 13, 18) in (*klebsiella spp.*)



**Figure14.** Effect of compound (9, 11, 13, 18) in (*escherichia. coli.*)



**Figure 17.** Effect of compound (8, 10, 12, 14) in (*rhizo.*)



**Figure 15.** Effect of compound (8, 10, 12, 14) in (*klebsiella spp.*)



**Figure 18.** Effect of compound (9, 11, 13, 18) in (*rhizo.*)

## Conclusion

A new Mannich bases were created through the reaction of caebazole, parahydroxybenzaldehyde, and various primary amines (1–5). The project was divided into two phases. The first portion involves

creating a monomer of Mannich bases through condensation reaction. The reaction occurs between aromatic aldehyde (P-hydroxy benzaldehyde) and primary amines like (1-5) with minor amines such as

Carbazol(A-E). By condensing Mannich bases made in part one with formaldehyde and phenol, the second stage included making phenol formaldehyde resin with Mannich bases (Aa-Ee) . The synthesized resins (Phenol-formaldehyde) have been characterized.

## Acknowledgment

I gratefully acknowledge to University of Baghdad/ College of Science for Women/ Department of Chemistry for help to do this study.

## Authors' Declaration

- Conflicts of Interest: None.
- I hereby confirm that all the Figures and Tables in the manuscript are mine. Furthermore, any Figures and images, that are not mine, have been included with the necessary permission for re-publication, which is attached to the manuscript.

Ultimately the examinations of FTIR, H-NMR and <sup>13</sup>C-NMR provided proof that the chemicals were prepared and also that to determine the degree of biological activity associated with some of the active groups and their antifungal properties were tested.

- Authors sign on ethical consideration's approval.
- Ethical Clearance: The project was approved by the local ethical committee at University of Baghdad.

## References

1. Perederic OA, Mountraki A, Papadopoulou E, Woodley JM, Kontogeorgis GM. Life Cycle Analysis of Phenol-Formaldehyde Resins Substituted with Lignin. *Comput Aided Chem Eng*. 2020 Jan 1; 48: 607-612. <https://doi.org/10.1016/B978-0-12-823377-1.50102-6>.
2. Lokhande PK, Sonigara KK, Jadhav MM, Patil DS, Soni SS, Sekar N. Multi-Dentate Carbazole Based Schiff Base Dyes with Chlorovinylene Group in Spacer for Dye-Sensitized Solar Cells: A Combined Theoretical and Experimental Study. *ChemistrySelect* 2019 Apr 16; 4(14): 4044-56. <https://doi.org/10.1002/slct.201803940>.
3. Çelik F, Süleymanoğlu N, Ustaş R, Bektaş E, Ünver Y. 1, 3-Bis (((E)-(9-ethyl-9H-carbazol-3-yl) methylene) amino) propan-2-ol: Synthesis, Characterization DFT Study, and Acetylcholinesterase Inhibitory Activity. *Russ J Phys Chem A*. 2023 May; 97(5): 981-988. <https://doi.org/10.1134/S0036024423050096>
4. Afrid ZH, Cahyana AH. Synthesis of carbazole derivative compound with the Mannich reaction and antioxidant activity. In *AIP Conf Proc* 2022 Oct 31; 2563(1). AIP Publishing. <https://doi.org/10.1063/5.0104131>
5. Verma N, Awasthi S, Jain V. Synthesis of N-mannich bases of some substituted carbazoles. *J Sci Technol*. 2022; 14(4): 208-12. <https://doi.org/10.52711/2349-2988.2022.00034>
6. Sharshira EM, Ataalla AA, Hagar M, Salah M, Jaremko M, Shehata N. Novel Novolac Phenolic Polymeric Network of Chalcones: Synthesis, Characterization, and Thermal-Electrical Conductivity Investigation. *Molecules*. 2022 Aug 24; 27(17): 5409. <https://doi.org/10.3390/molecules27175409>
7. Khammas S, Yosef S, Mahmood T, Mahmood W, Taher S, Hadi M. Synthesis and Characterization of Chelating Phenolic Polymers Containing Metoclopramide Hydrochloride Drug. *Egypt J Chem*. 2021 Sep 1; 64(9): 4973-4984. <https://doi.org/10.21608/ejchem.2021.44696.2908>
8. Emmanuel BD, Beevi J, Dharan SS. A concise review on carbazole derivatives and its biological activities. *J Pharm. Sci. Res*. 2020 Oct 1; 12(10): 1271-1277. <https://www.proquest.com/docview/2458969564>
9. Khammas SJ, Mahdi IS, Yousif SA. Synthesis, Characterization and Biological Evaluation of Esters Derived from Sulfamethoxazole Drug. *J Glob Pharma Technol*. 2019; 11(03): 478-486.
10. AL sahib SA, awad SH. Synthesis, Characterization of Chitosan para- hydroxyl Benzaldehyde Schiff Base Linked Maleic Anhydride and the Evaluation of Its Antimicrobial Activities. *Baghdad Sci J*. 2022 ; 19(6): 1265-1275. <https://doi.org/10.21123/bsj.2022.5655>
11. Khammas SJ, Hamood AJ. Synthesis, Cytotoxicity, Xanthine Oxidase Inhibition, Antioxidant of New Pyrazolo {3, 4 d} Pyrimidine Derivatives. *Baghdad Sci J*. 2019 Jul 2; 16(4 Supplement): 1003-1009. [https://doi.org/10.21123/bsj.2019.16.4\(Suppl.\).1003](https://doi.org/10.21123/bsj.2019.16.4(Suppl.).1003)
12. Auribie MA. Synthesis and Antibacterial Activity of Schiff Base Compounds Derived from Glyoxal,

- Vanillin with Their Complexes with Iron (III). Egypt J Chem. 2020 Oct 1; 63(10): 3985-3994. <https://doi.org/10.21608/ejchem.2020.31555.2699>
13. Patil SA, Patil SA, Ble-González EA, Isbel SR, Hampton SM, Bugarin A. Carbazole derivatives as potential antimicrobial agents. Molecules. 2022 Oct 4; 27(19): 6575. <https://doi.org/10.3390/molecules27196575>
14. Patil SA, Patil SA, Ble-González EA, Isbel SR, Hampton SM, Bugarin A. Carbazole Derivatives as Potential Antimicrobial Agents. Molecules. 2022 Oct 4; 27(19): 6575. <https://doi.org/10.3390/molecules27196575>

## تحضير وتشخيص بعض الراتنجات الدوائية باستخدام قواعد مانخ ودراسة الفعالية البيولوجية لها

تماضر علي محمود

قسم الكيمياء، كلية العلوم للبنات، جامعة بغداد، بغداد، العراق.

### الخلاصة

تم تحضير راتنج الفينول فورمالديهايد باستخدام قواعد مانخ للمجموعات الوظيفية والتي تعتبر مبتكرة في هذه الدراسة. يتضمن البحث مرحلتين. يتضمن الجزء الأول إنشاء مونومر لقواعد مانخ من خلال تفاعل التكثيف. يحدث التفاعل بين الألدهايد الاروماتي (باراهيدروكسي بنزليدهايد) والأمينات الأولية مثل (ميثوكلوبراميد ، تريميثوبريم ، 2-أمينوبنزوثيازول ، سلفاميثوكسازول ، و 4-أمينو أنتيبيريدين) مع أمينات ثانوية مثل كاربازول. من خلال تكثيف قواعد مانخ المصنوعة في الجزء الأول بالفورمالديهايد والفينول ، تضمنت المرحلة الثانية تحضير راتنج الفينول فورمالدهيد مع قواعد مانخ تم تمييز الراتنجات المركبة (الفينول فورمالديهايد). تم التشخيص بواسطة (H-NMR1 ، و FT-IR) لتحديد درجة الفعالية البيولوجية المرتبط ببعض المجاميع النشطة.

**الكلمات المفتاحية:** النشاط البيولوجي، كاربازول ، قواعد مانخ ، الراتنجات الصيدلانية ، فينول فورمالدهيد.